

**FAW3.3**Probe model **604-193**

Applications Measures electrically non-conducting coatings on non-ferrous metal base material (NC/NF). Suited for measurements on plane specimens or in pipes bore holes and recesses. Can possibly also be used when surfaces exhibit a damp condition (acidic contamination of test surface).

Examples • Paint, varnish or plastic coatings on aluminum, copper or brass (NC/NF)
The probe features a patented conductivity compensation. So that the different electrical conductivities of e.g. various aluminum alloys have no effect of the coating thickness measurement.

Probe design Single tip angle probe with spring-loaded measuring system

Applications NC/NF

Measurement range **Non-ferrous metal base materials (NF)**

0 ... 1200 μm / 0 ... 47.24 mils

Trueness **Non-ferrous metal base materials (NF)**

based on Fischer standards

0 ... 100 μm : $\leq 1 \mu\text{m}$
100 ... 800 μm : $\leq 1 \%$ of reading
800 ... 1200 μm : $\leq 3 \%$ of reading
0 ... 3.94 mils: $\leq 0.04 \text{ mils}$
3.94 ... 31.50 mils: $\leq 1 \%$ of reading
31.50 ... 47.24 mils: $\leq 3 \%$ of reading

Repeatability precision **Non-ferrous metal base materials (NF)**

based on Fischer standards

0 ... 100 μm : $\leq 0.5 \mu\text{m}$
100 ... 1200 μm : $\leq 0.5 \%$ of reading
0 ... 3.94 mils: $\leq 0.02 \text{ mils}$
3.94 ... 47.24 mils: $\leq 0.5 \%$ of reading

Influences **Aluminum base material**

The following values are valid for a reference coating thickness of 75 μm / 2.95 mils.

Curvature (R), measurement with reference to master calibration on flat surface

Measuring spot



Measurement error $\geq 10 \%$ for $R \leq 31 \text{ mm}$ / $R \leq 1.22 \text{ ''}$
Probe needs a minimum of $R = 13 \text{ mm}$ (support stand necessary) / $R = 0.51 \text{ ''}$

Curvature (R), measurement with reference to master calibration on flat surface


Measuring spot



Measurement error $\geq 10 \%$ for $R \leq 27 \text{ mm}$ / $R \leq 1.06 \text{ ''}$
Probe needs a minimum of $R = 1 \text{ mm}$ (support stand necessary) / $R = 39.37 \text{ mils}$

Edge distance (R), specification from probe pole center


Measuring spot in the center of the circular surface



No measurement error as of $R > 6 \text{ mm}$ / $R > 0.24 \text{ ''}$
Measurement error $\geq 10 \%$ for $R \leq 1.5 \text{ mm}$ / $R = 59.06 \text{ mils}$
Probe needs a minimum of $R = 1 \text{ mm}$ (support stand necessary) / $R = 39.37 \text{ mils}$

Edge distance (X), specification from probe pole center

Measuring spot




No measurement error as of $X > 2 \text{ mm}$ / $X > 78.74 \text{ mils}$
Measurement error $\geq 10 \%$ for $X \leq 1.2 \text{ mm}$ / $X \leq 47.24 \text{ mils}$

Influences **Aluminum base material**

The following values are valid for a reference coating thickness of 75 µm / 2.95 mils.

Base material thickness (D)

Measuring spot  Measurement error $\geq 10 \%$ for $D \leq 0.1 \text{ mm}$ / $D = 3.94 \text{ mils}$

Base material Influence of the el. conductivity of the base material (NF) in the range from 30 to 100 % IACS: deviation of the coating thickness is $\leq 2 \%$ valid for the total measurement range.

Admissible ambient temperature at operation - 10 °C ... + 40 °C / + 14 °F ... + 104 °F

Probe tip material Jewel tip

Probe tip replaceable Yes


Probe tip radius 1,2 mm / 47.24 mils

Measuring method Amplitude sensitive eddy current method according to ISO 2360, ASTM D7091, Non-conductive coatings on non-magnetic electrically conductive basis materials - Measurement of coating Thickness - Amplitude-sensitive eddy current method

Scope of supply Probe, metal plate ISO/NF for instrument check, calibration foils

Works with instruments All DUALSCOPE® and ISOSCOPE® hand-held instruments of the series FMP and FISCHERSCOPE® MMS® PC2 with F-Module PERMASCOPE®

Dimensions



Cable length: 1.50 m / 59.06 "

FE06 doc04/12